

Product Information

SITREN® SRA P 260

PRODUCT DESCRIPTION

SITREN® SRA P 260 is a powdered shrinkage reducing additive based on a polyether on an inorganic carrier.

Typical Properties

Property	Unit	Value
Appearance		Beige powder
Tamped Density	g/l	600

The data represents typical values (no product specification)

TYPICAL APPLICATIONS

SITREN® SRA P 260 effectively decreases the shrinkage of cementitious, dry-mix and specialty mortar formulations, that can occur when the formulation is losing moisture during the drying process. Main applications are

- Self-levelling mortars (SLU/SLO)
- Flowable screeds
- Tile adhesives
- Non-shrink grouts
- Repair mortars
- Waterproofing membranes
- Powder paints

Product Composition

Product Composition	Unit	Value
Moisture Content	wt%	≤4

The data represents typical values (no product specification)

BENEFITS & ADVANTAGES

SITREN® SRA P 260 functions by reducing capillary tension of pore water, a primary cause for drying shrinkage. In

addition SITREN® SRA P 260 provides the following benefits

- Superior reduction of drying as well as plastic shrinkage
- Reduced potential for slab curling
- Fast curing-almost no impact on initial setting and early strength development of cementitious binder system
- Very low contribution to VOC (volatile organic compound)-allows to formulate final products that meet e.g. EMICODE EC1^{PLUS} regulation
- Good workability properties
- Reduces the magnitude of capillary stresses and shrinkage strains
- Improved impermeability and durability
- Low impact on air void content of the mortar-no formula adjustment needed, good workability
- Excellent long-term stability in dry mortar formulations
- Easy-to-use powder (not hygroscopic)

Further information is available on request.

DOSAGE

Recommended dosage rates are 0.2 - 2 wt. % referred to total amount of dry components. Suitable screening tests are recommended prior to use.

HANDLING & PROCESSING

For production of the drymix mortar SITREN® SRA P 260 needs to be blended with the other dry ingredients by using standard mixing devices.

PACKAGING

Pallet à 360 kg (30 x 12 kg paper bags)

Pallets should be stacked two high maximum.

SHELF LIFE

SITREN® SRA P 260 may be stored in closed bags under dry conditions and below 35 °C for 12 months. It will remain safe to use for a longer period of time. Longer storage times may cause lumping which normally does not affect the performance of the product. However, product quality has to be verified by appropriate tests then.

HAZARDOUS SUBSTANCE

Information concerning

- Classification and labelling according to regulations for transport and for dangerous substances
- Protective measures for storage and handling
- Measures in case of accidents and fire
- Toxicity and ecological effects

is given in our material safety data sheets.

REGISTRATION LISTING SUMMARY

Based on the submitted information of our raw material suppliers we can confirm, that SITREN® SRA P 260 is compliant with EC Regulation 1907/2006 (REACH).

The relevant components of SITREN® SRA P 260 are listed/registered or exempt in the following chemical inventories:

Registration Listings

Registry	Status
Canada (DSL)	Yes
EU (EINECS/ELINCS)	Yes
Japan (ENCS)	Yes
USA (TSCA)	Yes

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third-party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH

Interface & Polyurethane Additives
Goldschmidtstraße 100
45127 Essen
Germany